

IN THE SPECIFICATION

Please replace the paragraph beginning at page 50, line 13, with the following rewritten paragraph:

The following composition was placed in a pressure kneader and was kneaded for 2 hours.

α -Fe magnetic powder	100 parts by mass
(Hc=1885Oe, Co/Fe=20at%, [[ss]] $\underline{\sigma_s}$ =138emu/g, BET=58m ² /g, average major axis length = 0.10 μ m)	
α -Al ₂ O ₃	6 parts by mass
(SUMITOMO CHEMICAL Co., Ltd., HIT-60A, average particle size = 0.20 μ m)	
α -Al ₂ O ₃	6 parts by mass
(SUMITOMO CHEMICAL Co., Ltd., HIT-82, average particle size = 0.13 μ m)	
Phosphoric ester	2 parts by mass
(TOHO CHEMICAL, PHOSPHANOL RE610)	
Binder solution	49 parts by mass